

**TPE/64 Santoprene® 101-64 schwarz Stärke 1 mm - 8 mm**

Stand: 06.2014

<b>Spezifisches Gewicht:</b>	0,97 g/cm <sup>3</sup> / ISO 1183
<b>Shorehärte:</b> 15 sec., 73°F (23°C), 0.0787 in (2.00 mm)	69° Shore A / ISO 868
<b>Temperaturbeständigkeit:</b>	-60 bis +135 °C
<b>Outdoor-Eignung:</b>	f1 / UL 746C
<b>Brandklasse:</b>	UL94 HB gelistet
<b>Beständigkeit gegen Reinigungsmittel:</b>	f3 / UL 749 + f4 / UL 2157
<b>Bemerkung:</b>	UL94 HB Zulassung, E80017 (1 mm)

**Jederzeitige Änderungen vorbehalten.**

**Alle in diesem technischen Datenblatt erhaltenen Angaben stellen Richtwerte dar, welche sich als langjährige Durchschnittswerte erprobt haben.**

**TPE/64 Santoprene® 101-64 black thickness 1 mm to 8 mm***Date: 06/2014*

<b>Specific Gravity:</b>	0,97 g/cm <sup>3</sup> / ISO 1183
<b>Hardness:</b> 15 sec., 73°F (23°C), 0.0787 in (2.00 mm)	69° Shore A / ISO 868
<b>Temperature resistance:</b>	-60 till +135 °C
<b>Outdoor-Suitability:</b>	f1 / UL 746C
<b>Fire class:</b>	UL94 HB listed
<b>Detergent Resistance:</b>	f3 / UL 749 + f4 / UL 2157
<b>Remarks:</b>	UL94 HB E80017 (1 mm)

**Subject to alteration.**

**All information obtained in this brochure as a guide, which have longterm experience average.**