

0171	EPDM 90° A, Stärke: 1 - 5 mm	Datum: 24.04.2020
<b>Härte DIN ISO 7619-1:</b>	90° ± 5° Shore A	
<b>Farbe:</b>	schwarz	
<b>Dichte:</b>	1,16 g/cm <sup>3</sup>	
<b>Temperaturbereich:</b>	-45° C bis +130° C, kurzfristig + 150° C	
<b>Druckverformungsrest ISO 815:</b>	24 h/ 70°C = < 20%	
<b>Spez. Durchgangswiderstand:</b>	VDE 0303 – 30 leitfähig	
<b>Reißfestigkeit ISO 37:</b>	> 10 N/ mm <sup>2</sup>	
<b>Reißdehnung ISO 37:</b>	> 100 %	
<b>Öl- &amp; Benzinbeständigkeit:</b>	nicht empfohlen	
<b>Säure- &amp; Laugenbeständigkeit:</b>	gut	
<b>Ozon- &amp; Witterungsbeständigkeit:</b>	gut	
<b>Ozonbeständigkeit ISO 1431-1 50 pph, 40° C, 72 h, 20 % Dehnung:</b>	ozonbeständig	
<b>Brandbeständigkeit FMVSS 302 geprüft bei 2 mm:</b>	B (schwer entflammbar)	
<b>Weiterreißwiderstand DIN ISO 34-1 A:</b>	> 2,5 N/ mm	
<b>Zulassungen:</b>	W270, WRAS (GB), ACS (F), KIWA (NL), Belgaqua (B), DIN EN 681-1/WA, WC	
<b>Bemerkungen:</b>	Nitrosaminfrei, RoHS II-konform, REACH konform, IMDS-Daten vorhanden 605638531; peroxidisch vernetzt	

Jederzeitige Änderungen vorbehalten. Es obliegt dem Besteller, vor Verwendung des Produktes selbst zu prüfen, ob es sich auf mögliche anwendungswirksame Einflüsse für den von ihm vorgesehenen Verwendungszweck eignet. Alle in diesem technischen Datenblatt enthaltenen Angaben stellen Richtwerte dar.

---

<b>0171</b>	<b>EPDM 90° A, thickness: 1 - 5 mm</b>	<b>date: 24.04.2020</b>
<b>hardness DIN ISO 7619-1:</b>	90° ± 5° Shore A	
<b>color:</b>	black	
<b>density:</b>	1,16 g/cm <sup>3</sup>	
<b>temperature range:</b>	-45° C bis +130° C short term + 150° C	
<b>compression set ISO 815:</b>	24 h/ 70°C = < 20%	
<b>spec. contact resistance:</b>	VDE 0303 – 30 conductive	
<b>tear strength ISO 37:</b>	> 10 N/ mm <sup>2</sup>	
<b>elongation at break ISO 37:</b>	> 100 %	
<b>oil and gasoline resistance:</b>	not recommended	
<b>Acid and alkali resistance:</b>	good	
<b>ozone and weather resistance:</b>	good	
<b>ozone resistance ISO 1431-1 50 pph, 40° C, 72 h, 20 % stretch:</b>	ozone resistant	
<b>fire resistance FMVSS 302 tested at 2 mm:</b>	B (flame retardant)	
<b>tear resistance DIN ISO 34-1 A:</b>	> 2,5 N/ mm	
<b>permissions:</b>	W270, WRAS (GB), ACS (F), KIWA (NL), Belgaqua (B), DIN EN 681-1/WA, WC	
<b>remarks:</b>	nitrosamine free, RoHS II compliant, REACH compliant, IMDS data available 605638531, peroxide linked	

---

We reserve the right to make changes at any time. Before using the product, it is the responsibility of the purchaser to check for himself whether it is suitable for his intended use with regard to possible influences affecting the application. All data contained in this technical data sheet are approximate values.

---